SPECIFICATION CONTROL DRAWING

10613



.0250

(.635 mm)

 $.048 \pm .002$

 $(1.22 \pm .05 mm)$

.032

(.813 mm)

.113

(2.87 mm)

.130

(3.30 mm)

.146 (3.71 mm)

(nominal)

.154 (3.91 mm)

(maximum)

77 OHM, AWG 24, 19 STRANDS OF AWG 36, OPTIMIZED DOUBLE SHIELDS, DATA BUS CABLE, MIL-STD-1553

Date: 3-5-15 S Revision:

THIS SPECIFICATION SHEET FORMS A PART OF THE LATEST ISSUE OF RAYCHEM SPECIFICATION 1200.

CONSTRUCTION DETAILS

ELECTRICAL CHARACTERISTICS

DIMENSIONS ARE NOMINAL VALUES IN INCHES. UNLESS OTHERWISE

CHARACTERISTIC IMPEDANCE 77 ± 5 ohms, Method C at 1 MHz MUTUAL CAPACITANCE 30.0 pF/ft. (98.4 pF/m) (maximum) ATTENUATION 1.4 dB/100 ft. (4.59 dB/100 m) (maximum)

at 1 MHz

SURFACE TRANSFER IMPEDANCE 10 milliohms/meter (maximum)

(Per SAE AS85485)

at 30 MHz

FILLERS

Modified ETFE

Modified FTFF

CONDUCTORS

AWG 24,

19 Strands of AWG 36, Silver-Coated High-Strength Copper Alloy **DIELECTRICS**

Radiation-Crosslinked,

Colors - Light Blue/White

Radiation-Crosslinked,

COMPONENT WIRE PRIOR TO CABLING (Test procedures per SAE AS22759)

ADDITIONAL REQUIREMENTS

CONDUCTOR RESISTANCE 26.5 ohms/1000 ft. (86.9 ohms/km) (nominal)

CROSSLINKING PROOF TEST $300 \pm 3^{\circ}$ C for 1 hour, .625 inch (15.9 mm) mandrel. .375 lb (170 g), 2.5 kV dielectric test

INSULATION (DIELECTRIC)

ELONGATION 50% (minimum)

5000 lbf/in² (34.5 N/mm²) (minimum) TENSILE STRENGTH

NSULATION FLAWS

SPARK TEST 3.0 kV (rms) IMPULSE TEST 8.0 kV (peak)

5000 megohms for 1000 ft. INSULATION RESISTANCE (1524 megohms-km) (minimum)

LOW TEMPERATURE-COLD BEND $-65 \pm 3^{\circ}$ C for 4 hours,

.750 inch (19.1 mm) mandrel, 1.00 lb (454 g), 2.5 kV dielectric test

SHRINKAGE 200 ± 3°C for 1 hour,

.125 inch (3.18 mm) (maximum)

in 12 inches (305 mm)

1st SHIELD AWG 38, Tin-Coated Copper,

2nd SHIELD

AWG 38,

Optimized

JACKET

Optimized

Tin-Coated Copper,

Radiation-Crosslinked,

Modified ETFE

FINISHED CABLE

(Test procedures per NEMA WC 27500, unless otherwise specified)

BLOCKING 200°C for 6 hours

CABLE LAY LENGTH .75 inch (19.1 mm) (minimum), 1.25 inches (31.8 mm) (maximum)

CROSSLINKED VERIFICATION $300 \pm 5^{\circ}$ C for 6 hours,

6.00 inch (152 mm) mandrel FLAMMABILITY 3 seconds (maximum);

3 inches (76.2 mm) (maximum); (Method B of Spec 1200) no flaming of facial tissue

ELONGATION 50% (minimum)

5000 lbf/in² (34.5 N/mm²) (minimum) TENSILE STRENGTH

JACKET FLAWS SPARK TEST

1.0 kV (rms) IMPULSE TEST 6.0 kV (peak)

JACKET THICKNESS .008 inch (.203 mm) (nominal)

LOW TEMPERATURE-COLD BEND -55 ± 5 °C for 4 hours.

6.00 inch (152 mm) mandrel

VOLTAGE WITHSTAND (DIELECTRIC)

1500 volts (rms)

Designate outer jacket color with a dash number in accordance with MIL-STD-681. Unless otherwise specified, outer jacket color will be white (designated by a "-9" appended to the part number and

conductor AWG size, e.g. 10613-24-9). Other codes and suffixes may be added to the part number, as necessary, to capture any additional requirements imposed by the purchase order.

WEIGHT 26.2 lbs/1000 ft. (39.0 kg/km) (maximum)

CABLE IDENTIFICATION: Outer jacket shall be marked in contrasting color at 12 inch (305 mm) (nominal) intervals between marks as follows: "10613 RAYCHEM"

ENGINEERING REFERENCE

TEMPERATURE RATING 150°C (maximum)

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. Tyco Electronics Corporation also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

Page 2 is for internal use only

Cheminax, Raychem, TE Connectivity, TE connectivity (logo), and TE (logo) are trademarks.

